

Allure™ Décor Photo Panels

Product Description

Allure Décor Photo Panels for dye sublimation inks are available in a wide range of sizes from 8" x 10" to 4' x 8'. Cut sheets are routed with a smooth clean edge and rounded corners to make handling safe and easy. All sheets are also covered with a low-tack release liner which help to protect the coating from UV exposure.

Allure dye sublimation is available in a high gloss, white finish. Satin, matte, clear/brushed and other exciting finishes are coming soon!



Physical Specifications

| | |
|-------------------|------------------------------------|
| Material Type | Sublimatable White Coated Aluminum |
| Thickness | 0.045" (1.2 mm) |
| Gloss Level | 89% (High Gloss) |
| Whiteness | 110 |
| Back Surface | Smooth Epoxy |
| CIE Color (F7/2°) | L*95.9 / a* 1.8 / -9.0 |
| Temperature | 390°F |
| Dwell Time | 90 Seconds |
| Pressure | 100psi |

Additional Information

| | |
|-------------|--|
| Storage: | 70°F (21°C) / 50% Relative Humidity; store in original packaging and in a controlled environment |
| Shelf Life: | Minimum 1 year from purchase date, when stored as specified |
| Lamination: | Not required |

Printer Compatibility & Handling

| | |
|----------------------------|---|
| Printer Compatibility | Most printers using dye sublimation ink (both converted and OEM) |
| Ink Compatibility: | Most dye sublimation inks |
| Optimal Print Environment: | 70°F (21°C), 30-60% Relative Humidity |
| Handling: | Avoid touching the coated surface. Cotton gloves should be used when handling inkjet coated materials from Breathing Color. Note: the white, printable surface of Allure is protected by a release liner that must be removed before printing. |

Note: Actual print stability will vary according to media, printed image, display conditions, light intensity and atmospheric conditions. Breathing Color does not guarantee the longevity of prints. For maximum print life display all prints under glass or lamination or properly store them. All of the descriptive information and recommendations for the use of Breathing Color products should be used only as a guide. Furnishing such information and recommendations shall in no event constitute a warranty of any kind by Breathing Color. All purchasers of Breathing Color products shall independently determine the suitability of the material for the purpose for which it is purchased. Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Neither the seller nor manufacturer shall be liable either in tort or in contract for any loss of damage, direct, incidental or consequential (including loss of profits or revenue) arising out of the use of or the inability to use the product. No statement or recommendation not contained herein shall have any force or effect unless in agreement signed by officers of seller and manufacturer.